

RHINO TUFF STUFF

SPRAY APPLIED WATERPROOF MEMBRANE

| Process: | Product: | Pack Size: | Coverage Rate: | Typical Recoat times * |
|---|--|--|---|---|
| Primer for concrete, timber and polyurethane cove | Rhino Prime 150 (PC760/PC765 or PC770/PC775) | 10 litre or 40 litre kits | 6-10 m ² per Litre Multiple coats may be required depending on porosity of the substrate | 3-4 hours @ 20°C |
| Treatment of Joints with Bandage system or Use bond-breaker tape | Rhino CS Elastomeric Basecoat Bandage 100mm | 1 & 5 US gallon pails 91 metre rolls | 74 metres per gallon @125mm width 91 metres per length | 12-16 hours @ 20°C and 75% humidity |
| | Rhino Elastomeric Basecoat Bond-breaker tape | 1 & 5 US gallon pails metre rolls | 74 metres per gallon @125mm width m per roll | Not applicable |
| Coving rubber with contact adhesive | Rhino coving (CON107) 3M 75 Repositionable Spray Adhesive, 3M 76 High Tack or 3M 77 Multipurpose Adhesive | 15 metre coils Spray cans | 15 metres per length | 30-60 minutes @ 20°C |
| Or Polyurethane Sealant cove | Sika 11FC | 310mL cartridge or 600mL sausages | 7.5 metres per litre for a 50mm radius coving | 50mm radius cove 16 hours @ 20°C and 75% humidity |
| Waterproofing Membrane | Rhino Tuff Stuff (TS10250/TS10204 or TS10075/TS10062) | 199kg or 658 kg kits | Minimum 2.4mm thickness 2.7-2.8Kgs per m ² | Upto 4 hours @ 20°C and 75% humidity |
| Optional aggressive non-slip | Rhino Tuff Stuff with Alox aggregate (TC340 or TC345) | 5 kgs | As required* | |
| UV resistant flexible polyurethane topcoat with standard non-skid particles (TC330) | Rhino Aliphatic Topcoat, Rhino Armafloor 500, Unithane PU, Vulkem 346 Topcoat | 5 litre kit, 10 or 40 litre kits, 5 litre kit, 5US gal kit. | 4-5 m ² per litre, 5-6 m ² per litre, 4-5 m ² per litre, 75-90 m ² per pail. | 1 - 4 hours @ 20°C and 75% humidity |

* For use on pedestrian ramps and where there is ponding.

* Recoat times dependent on ambient and substrate temperature, humidity, film builds etc.

Rhino Linings Australasia Pty Ltd
501-505 Olsen Avenue, Molendinar Qld 4214 Australia
Ph: +61 7 5585 7000 ~ Fax: +61 7 5539 6399
info@rhinolinings.com.au

Oct2022

POLYMER GROUP LTD
PO Box 204 106 Highbrook, Auckland 2161, New Zealand
Telephone: 64-9-274 1400 Fax: 64-9-274 1405
Email: sales@polymer.co.nz www.polymer.co.nz