

VULKEM 350/346

LIQUID APPLIED WATERPROOF MEMBRANE

Process:	Product:	Pack Size:	Coverage Rate:	Typical Recoat times *
Primer for dry concrete & timber substrates.	Vulkem 171	5 US gal pails	6-10 m ² per Litre Multiple coats may be required depending on porosity of the substrate	1-2 hours @ 20°C
Treatment of Joints with Polyester fibre tape	Vulkem 350R Tape 100-150mm	5 US gallon pails 50 metre rolls	30 lineal metres per gallon @125mm width 50 metres per roll	12-16 hours @ 20°C and 75% humidity
Coving rubber with Polyurethane Sealant	Sika 11FC	310mL cartridge or 600mL sausages	7.5 metres per litre for a 50mm radius coving	50mm radius cove 16 hours @ 20°C and 75% humidity
Waterproofing Membrane	Vulkem 350SL or Vulkem 350R on vertical & slopes	5 US gallon pails	18.9m ² per pail. Minimum 0.75mm DFT.	12-16 hours @ 20°C and 75% humidity
<i>Optional aggressive non-slip</i>	Walton Park 18/36	25 kgs	<i>As required*</i>	
UV resistant flexible polyurethane topcoat	Vulkem 346 Topcoat Rhino Armafloor 500	5US gal kit, 10 or 40 litre kits.	40-50 m ² per pail, 3.5-4 m ² per litre.	2 - 8 hours @ 20°C and 75% humidity

* Recoat times dependent on ambient and substrate temperature, humidity, film builds etc.

Rev 1 Oct2022

POLYMER GROUP LTD

PO Box 204 106 Highbrook, Auckland 2161, New Zealand
Telephone: 64-9-274 1400 Fax: 64-9-274 1405
Email: sales@polymer.co.nz www.polymer.co.nz