



Australia's National
Science Agency

Assessment of:
AS 4654.1:2012

Enviro 700x
Waterproofing membranes for external
above-ground use Part 1: Materials

Prepared for:	Ryan Steele
Author:	Khanh Ho
Date of issue:	14/11/2022
Report number:	8454
CSIRO agreement No:	TEMP 20220523

Commercial-in-confidence

Term of validity: This CSIRO waterproofing membranes for external above-ground use report will retain validity for three years after the date of issue. Revalidation/reassessment is required to extend conformity beyond this date.



Prepared on behalf of CSIRO by

Name	Khanh Ho
Position	Capability Lead – Slips and Membranes
Date	14/11/2022
Signature:	

CSIRO Infrastructure Technologies

Materials Performance
Research Way
CLAYTON, VIC 3168
AUSTRALIA
Telephone: 1300 363 400
EnquiriesTeam@csiro.au
www.csiro.au

Use of Reports**Use of Reports – Testing**

This report is subject to binding obligations under which it was prepared. In particular, the Report must not be used:

1. As a means of endorsement; or,
2. In a company prospectus or notification to a Stock Exchange document for capital raising, without the prior written consent of CSIRO.

The Report may be published verbatim and in full, provided that a statement is included on the publication that it is a copy of the Report issued by CSIRO.

Excerpts of the Report may not be published.

Use of Reports – Consultancy

This report is subject to binding obligations under which it was prepared. In particular, the Report may only be used for the following purposes:

1. The information in the Report may be used by the party that commissioned the Report for its internal business operations (but not licensing to third parties);
2. The report may be copied for distribution within the organisation that commissioned the Report;
3. Copies of the Report (or extracts of the Report) may be distributed to contractors and agents of the organisation that commissioned the Report who have a need for the Report for its internal business operations. Any extracts of the Report distributed for this purpose must clearly note that the extract is part of a larger Report held by the organisation that commissioned the Report and which has been prepared by CSIRO.

The name, trade mark or logo of the CSIRO must not be used without the prior written consent of CSIRO.

Copyright and disclaimer

© 2022 CSIRO To the extent permitted by law, all rights are reserved and no part of this publication covered by copyright may be reproduced or copied in any form or by any means except with the written permission of CSIRO.

Important disclaimer

CSIRO advises that the information contained in this publication comprises observations based on test results. The reader is advised and needs to be aware that such information may be incomplete or unable to be used in any specific situation. No reliance or actions must therefore be made on that information without seeking prior expert professional, scientific and technical advice. To the extent permitted by law, CSIRO (including its employees and consultants) excludes all liability to any person for any consequences, including but not limited to all losses, damages, costs, expenses and any other compensation, arising directly or indirectly from using this publication (in part or in whole) and any information or material contained in it.

Limitation

The results reported herein relate only to the item(s) tested.

Customer

Waterproofing Technologies Pty Ltd
295 Princes Hwy
St Peters 2044 NSW Australia

Statement of Conformity

This Assessment report documents the results and assessments of products produced by,
Waterproofing Technologies Pty Ltd
295 Princes Hwy
St Peters 2044 NSW Australia

Submitted and designated as follows,

Enviro 700x

The products as submitted confirmed with the specified requirements of the following criteria,

AS 4654.1:2012

Contents

1. Executive Summary	6
2. Introduction	7
3. Test specimen description	8
4. Test Methodology	9
4.1 ASTM E96/E96M – 16 Water Vapour Transmission of materials	9
4.2 AS4654.1-2012 Appendix B Resistance to cyclic movement	9
4.3 AS 4654.1-2012 Appendix A Durability of membrane and Temperature Resistance	9
4.4 ASTM C794:2018 Standard test method for adhesion-in-peel of elastomeric joint sealants	10
4.5 AS/NZS 4347.9:1995 (Reconfirmed) 2014 Damp-proof courses and flashings—Methods of test, Method 9: Determining thickness.....	10
5. Results	11
5.1 ATSM E96/E96M - 16 Water Vapour Transmission of materials	11
5.2 AS 4654.1:2012 Appendix B Resistance of waterproofing membranes to cyclic movement	12
5.3 AS 4654.1:2012 Appendix A Durability of membrane	13
5.4 ASTM C794:2018 Standard test method for adhesion-in-peel of elastomeric joint sealants	18
5.5 AS/NZS 4347.9:1995 (Reconfirmed) 2014 Damp-proof courses and flashings—Methods of test, Method 9: Determining thickness.....	19
6. Comments.....	20

Figures

Figure 1 Top face of Enviro 700x	8
Figure 2 Underside of Enviro 700x	8
Figure 3 Images of test sample performing durability load / elongation test	17
Figure 4 Images OF test sample performing Adhesion-In-Peel	18

Tables

Table 1 Summary of test requirements and test specimen results for AS4654.1:2012.....	6
Table 2 Details of submitted test specimen	7
Table 3 Details of the schedule for testing of the submitted specimen	7
Table 4 Water Vapour Transmission test results	11
Table 5 Test sample holing during cyclic movement and test results.....	12
Table 6 Durability test results - Control	13
Table 7 Durability test results – Water immersion	14
Table 8 Durability test results – Detergent immersion	15
Table 9 Durability test results – Heat Ageing	16
Table 10 Durability test results - Temperature resistance	16
Table 11 Adhesion-in-Peel Strength test results	18
Table 12 Determining Thickness test results.....	19

1. Executive Summary

Test Standard: Testing was conducted on a waterproofing membranes for external above-ground use with fully bonded membrane liquid non-exposed to assess its performance for: water vapour transmission; acceptance of cycle movement; durability; bond strength and thickness. The external waterproofing membranes properties were tested in accordance to the Australian Standard AS4654.1:2012.

All methods were carried out according to Tables 2.1 under fully bonded membrane liquid non-exposed against the performance criteria of Tables A1, A3 and A4.

Test results: The waterproofing membrane presented for testing complied with the performance criteria set in AS4654.1:2012 waterproofing membrane for external above-ground, non-exposed. The following table shows the Enviro 700x performance as assessed from testing.

TABLE 1 SUMMARY OF TEST REQUIREMENTS AND TEST SPECIMEN RESULTS FOR AS4654.1:2012

TEST	METHOD	REQUIREMENTS	RESULT
(a) Moisture Transmission Rate	ASTM E 96 Desiccant method for Determining Water Vapour Transmission (WVT)	Record result	WVT 16.80 g/m ² /24hrs Permeance 115.40 ng/Pa.s.m ²
(b) Acceptance of movement	AS AS4654.1 Appendix B for assessment of cyclic movement of membrane	Pass or fail criteria by observing any cracking, rupture holing or extending through the thickness for more than 1 mm in from the edge of the specimen.	Class III
(c) Durability 1. Control 2. Water immersion 3. Detergent immersion 4. Heat ageing at 80°C 5. Temperature resistance at -15°C to +85°C	AS4654.1 Appendix A for assessment of membranes durability AS4654.2 temperature resistance section 2.4.2 (c)	Pass or fail criteria; compared to control samples: elongation at break shall be not less than 25 % for water and detergent immersion. Whereas, elongation at break shall be not less than 50 % for heat ageing samples.	1. Class III 2. Class III 3. Class III 4. Class III 5. Class III
(d) Bond strength to concrete substrate	ASTM C794 Standard test method for adhesion-in- peel of elastomeric joint sealants	Test samples exposed to dry conditions, then tested for adhesion-in-peel strength.	Mean of 172.71 N with one test specimen 30% adhesive failure loss for concrete and 70% mesh failure. Another one specimen with 100% Cohesive failure for concrete. Last two specimens with 100% adhesive failure loss respectively.
(e) Membrane thickness	AS/NZS 4347.9:1995 (Reconfirmed) 2014 Damp- proof courses and flashings.	The film thickness shall be measured at a minimum of five points and a maximum of 10 points, equally spaced across the strip	1.35 mm

Note: The above is only a summary of the overall results, and must be read in conjunction with the relevant sections of this report.

2. Introduction

CSIRO Services was engaged to assess a waterproofing membrane for compliance against the AS4654.1:2012 according to Table 2.1 under fully bonded membrane liquid, non-exposed with compliance confirmed against the performance criteria of Tables A1, A3 and A4. The details for this assessment are listed in Table 3 below.

TABLE 2 DETAILS OF SUBMITTED TEST SPECIMEN

CSIRO Agreement No.:	TEMP 20220523
TEST SPONSOR:	Waterproofing Technologies Pty Ltd
PRODUCT DESCRIPTION:	Enviro 700x
SPECIMEN RECEIVED DATE:	17/06/2022

Note: CSIRO accepts no responsibility for the selection of specimens. The results in this report apply to the specimens tested and may not be applicable to other specimens of the same product.

This report details the performance, testing conditions and outcomes of the specimen assessed in accordance with waterproofing membrane system for exterior use - above ground level. Table 3 details the sponsor's specified schedule of tests for the product.

TABLE 3 DETAILS OF THE SCHEDULE FOR TESTING OF THE SUBMITTED SPECIMEN

CSIRO Agreement No.:	2020123192
TEST SCHEDULE:	AS4654.1 Clause A2, A4 Tables A1, A3 & A4: a) Moisture vapour transmission rate - ASTM Designation E96/E96M – 16, 'Standard Test Methods for Water Vapour Transmission'; b) Acceptance of cyclic movement; Appendix B 'Assessment of resistance of waterproofing membranes to cyclic movement'; c) Durability - Appendix A 'Assessment of durability of waterproofing membranes: Table A4 (a) Controls Table A4 (b) Water immersion Table A4 (c) Detergent immersion Table A1 & A4 (d) Heat aging at 80°C d) Temperature resistance at -15°C to +85°C e) Bond strength to concrete substrate - ASTM C794:2018 Standard test method for adhesion-in-peel of elastomeric joint sealants. f) Membrane thickness – AS/NZS 4347.9:1995 (Reconfirmed) 2014 Damp-proof courses and flashings.

Enviro 700x - 8454

3. Test specimen description

The Enviro 700x supplied by Waterproofing Technologies Pty Ltd is single component, low odour, moisture cured polyurethane elastomer waterproofing system. The nominal size of the membrane was 300 mm wide, 300 mm length and 1.40 mm thick.

The supplied specimen for assessment is shown below in Figures 1 and 2.



FIGURE 1 TOP FACE OF ENVIRO 700X



FIGURE 2 UNDERSIDE OF ENVIRO 700X

4. Test Methodology

4.1 ASTM E96/E96M – 16 Water Vapour Transmission of materials

This Standard outlines the method for determining water vapour transmission (WVT) through the membrane using the desiccant and dummy sample method. Four test samples were prepared by mechanical sealed using two neoprenes and a teflon gasket placed onto the open side of the test cups. The test cups contain dried desiccant with the trafficable side facing up were placed in a climate-controlled environment with periodic weighing so that the rate of water vapour movement through the membrane to the desiccant can be determined.

The exposed area (test dish face) for each of the cups was 0.002827 m². The test cups (all except the dummy sample, no desiccant) had a 6 mm gap between the desiccant and the underside of the membrane.

All test assemblies were kept in a Steridium environmental where chamber temperature humidity are maintained at a temperature of 23 ±2°C and 60 ±5% relative humidity, for the 47 days duration. Measurements taken each afternoon (excluding weekends) over this period to determine the weight change and permeance of the membrane.

4.2 AS4654.1-2012 Appendix B Resistance to cyclic movement

This Standard outlines the method for determining resistance of membrane to cyclic movement set at maximum strain used for the cycling shall be 4mm of extension.

A rectangular test sample of 65 mm x 25 mm x 1.36 mm was cut from the Enviro 700x, then held in the test grips (70(w) x 45(l) x 20(t) mm), exposing a 25 x 2 mm central portion of the sample.

An Applied Test Systems Series 904 Vertical Sealant Tester was used for testing. The vertical sealant testing machine used software for cyclic movement control. The vertical testing machine was set to elongate the clamped test sample for the cycling is 4 mm extension. Once the test piece reached full extension, it then returned to its original position, which completed one cycle of movement. The elongation and return was then repeated to complete a 50 cycle movement test, each cycle conducted over a nominal 2 hour period.

The test sample was inspected for signs of breakage or cracks and measured for any necking. A reduction in width of more than 1 mm inwards from the edge of the test sample constitutes a failure.

4.3 AS 4654.1-2012 Appendix A Durability of membrane and Temperature Resistance

This Standard outlines the method for determining resistance of the membrane's durability after conditioning in various solutions over set periods, then assessed against an unconditioned material.

Testing of the Enviro 700x was in accordance with Appendix A4.2 Durability of membranes. As specified in A2.2.1 the membrane test samples were prepared in accordance with AS 1145.3-2001, Type 2, strip samples 10mm width with a 50mm gauge length. Test samples were exposed and conditioned to those requirements specified in Table A1, A4 & Temperature Resistance of AS4654.1-2012.

In accordance with A4.2.2.2 Testing, a universal testing machine, fitted with a calibrated 5kN load cell, was used to record the elongation at break and tensile strength. The test rate of 200 mm/min used for testing elongation at break of the immersed test samples were compared to the control test samples. (Note: Set grips at 50mm for initial distance (L) due to extensometer max out of 250mm travel.)

4.4 ASTM C794:2018 Standard test method for adhesion-in-peel of elastomeric joint sealants

This test method consists of preparing four strip test specimens of 25mm width and 250mm in length by embedding a wire mesh screen between two thin layers of Enviro 700x on to the surface of concrete substrate. All adhesion-in-peel test specimens were prepared by the manufacturer per ASTM C794:2018 procedure. Enviro Prime SB is a universal solvent-based primer first apply on surface of concrete substrate per manufacturer's procedure, follow with Enviro 700x. For each coating, remix briefly before applying strips only 100mm in length on to the surface of concrete substrate to ensure good initial bond at a temperature of $23 \pm 2^{\circ}\text{C}$ and $60 \pm 5\%$ relative humidity, for the 21 days duration. Then the specimens were placed in a tension-testing machine in such a way the test sample is peeled back from the substrates at 180° to the face of the sample. The exerted force was measured as well as the mode of failure of the membrane from both substrates at the test rate of 50mm/min for 1 minute.

4.5 AS/NZS 4347.9:1995 (Reconfirmed) 2014 Damp-proof courses and flashings— Methods of test, Method 9: Determining thickness

This Standard sets out a means to determining the thickness of polyethylene film. All three rectangular test strips of 290 mm x 50 mm was cut across middle width of supplied sheets. The sheet thickness measured a three points, equally spaced across the strip. The specimens were tested in a conditioning room maintained at a temperature of $23 \pm 2^{\circ}\text{C}$ and $60 \pm 5\%$ relative humidity.

5. Results

5.1 ATSM E96/E96M - 16 Water Vapour Transmission of materials

The periodic measurements of the membrane test samples were recorded as shown in Table 4, below.

	In	Out
Date of Preconditioning:	12/08/2022	19/08/2022
Date of test:	19/08/2022	05/10/2022

TABLE 4 WATER VAPOUR TRANSMISSION TEST RESULTS

Specimens No.	Water Vapour Transmission (g/m ² 24hr)	Permeance (ng/Pa.s.m ²)
8454/57	16.49	113.26
8454/58	17.02	116.86
8454/59	16.90	116.07
Average	16.80	115.40

The performance criteria set out in AS4654.1 – 2012, Table A3 to record result, specifies a water vapour transmission rate shall determine if material is a moisture suppressant coating.


Enviro 700x - 8454

5.2 AS 4654.1:2012 Appendix B Resistance of waterproofing membranes to cyclic movement

The test result for cyclic movement of the waterproofing membrane test sample is shown in Table 5 below. The test sample completed 50 cycles for the nominal 2 hour period.

	In	Out
Date of Preconditioning:	12/08/2022	19/08/2022
Date of test:	19/08/2022	23/08/2022

TABLE 5 TEST SAMPLE HOLING DURING CYCLIC MOVEMENT AND TEST RESULTS

Specimen No.:	8454/48	
Test specimen	Test specimen 65 (l) mm x 25 (w) mm x 1.36 (t) mm section	
Membrane Classification	CLASS III	
Elongation at break:	Maximum strain used for the cycling shall be 4mm of extension	
Clamped test specimen of cyclic test:		
Observations		
Day 1		
Day 2		
Day 3		
Day 4		
Surface Defects		
Crazing		
Surface Tear		
Membrane Rupture		
Final Result	PASS	50 cycles

The performance criteria set out in AS4654.1:2012, Table A3 and section B4, pass or fail criteria by observing any cracking, rupture or necking of more than 1 mm down from original width.

5.3 AS 4654.1:2012 Appendix A Durability of membrane

The tensile strength and elongation at break were recorded for the control and immersed test samples. Criteria for pass or failure of the immersed test samples were then compared to the control samples. AS 4654.1:2012 Table A2 joint movement bond breaker was also referenced in Table 6, below.

	In	Out
Date of Preconditioning:	27/07/2022	12/08/2022
Date of test:	12/08/2022	12/08/2022

TABLE 6 DURABILITY TEST RESULTS - CONTROL

Control Specimens						
	Break Force (N)	Thickness (mm)	Tensile strength (F/A) (MPa)	Elongation at break		Class
				(mm)	(%)	
8454/01	34.53	1.35	2.56	357.38	715	III
8454/02	50.02	1.44	3.47	449.81	900	
8454/03	36.19	1.43	2.53	339.77	680	
8454/04	43.14	1.35	3.20	387.55	775	
8454/05	40.26	1.35	2.98	364.36	729	
Average	40.83	1.38	2.95	379.77	760	

Table A1: Classification of Membranes

CLASS I – Elongation at break <60%

CLASS II – Elongation at break 60-299%

CLASS III – Elongation at break ≥300%

Class III membrane, a 12mm wide bondbreaker/tape should be applied over a joint to accommodate the joint opening by up to 5 mm.

Water Immersion

	In	Out
Date of Preconditioning (7D):	8/08/2022	15/08/2022
Date in Water (7D):	15/08/2022	22/08/2022
Date of Test (7D):	22/08/2022	-
Date of Preconditioning (28D):	8/08/2022	15/08/2022
Date in Water (28D):	15/08/2022	12/09/2022
Date of Test (28D):	12/09/2021	-
Date of Preconditioning (56D):	8/08/2022	15/08/2022
Date in Water (56D):	15/08/2022	10/10/2022
Date of Test (56D):	10/10/2022	-

TABLE 7 DURABILITY TEST RESULTS – WATER IMMERSION

Water Immersion Specimens						
	Average Break Force (N)	Average Thickness (mm)	Average Tensile strength (F/A) (MPa)	Average Elongation at break		PASS/FAIL
				(mm)	(%)	
7 day period	31.61	1.42	2.22	505.41	1011	PASS
28 day period	27.38	1.41	1.94	471.50	943	PASS
56 day period	21.53	1.41	1.53	446.84	894	PASS
Observations:						
7 day period	No defect					
28 day period	No defect					
56 day period	Ne defect					
Table A4: Pass / Fail and Criteria compared with control samples						
PASS – Elongation at break shall not be less than 25% retention of elongation at break of the controls						

Detergent Immersion

	In	Out
Date of Preconditioning (7D):	8/08/2022	15/08/2022
Date in Water (7D):	15/08/2022	22/08/2022
Date of Test (7D):	22/08/2022	-
Date of Preconditioning (28D):	8/08/2022	15/08/2022
Date in Water (28D):	15/08/2022	12/09/2022
Date of Test (28D):	12/09/2021	-
Date of Preconditioning (56D):	8/08/2022	15/08/2022
Date in Water (56D):	15/08/2022	10/10/2022
Date of Test (56D):	10/10/2022	-

TABLE 8 DURABILITY TEST RESULTS – DETERGENT IMMERSION

Detergent Immersion Specimens						
	Average Break Force (N)	Average Thickness (mm)	Average Tensile strength (F/A) (MPa)	Average Elongation at break		PASS/FAIL
				(mm)	(%)	
7 day period	16.90	1.39	1.22	397.79	796	PASS
28 day period	17.42	1.38	1.26	394.76	790	PASS
56 day period	17.22	1.38	1.25	373.25	747	PASS
Observations:						
7 day period	No defect					
28 day period	No defect					
56 day period	Ne defect					
Table A4: Pass / Fail and Criteria compared with control samples						
PASS – Elongation at break shall not be less than 25% retention of elongation at break of the controls						

Enviro 700x - 8454

Heat Ageing

	In	Out
Date of Preconditioning:	9/08/2022	16/08/2022
Date in Oven:	16/08/2022	30/08/2022
Date of Test:	1/09/2022	-

TABLE 9 DURABILITY TEST RESULTS – HEAT AGEING**Heat Ageing @80 °C**

	Average Break Force (N)	Average Thickness (mm)	Average Tensile strength (F/A) (MPa)	Average Elongation at break		PASS/FAIL
				(mm)	(%)	
14 day period	23.37	1.36	3.13	528.27	1057	PASS

Observations: No defect

Table A4: Pass / Fail and Criteria compared with control samples

PASS – Elongation at break shall not be less than 50% retention of elongation at break of the controls

Temperature Resistance

	In	Out
Date of Preconditioning:	9/08/2022	16/08/2022
Date in Oven (85°C):	16/08/2022	23/08/2022
Date of Test:	25/08/2022	-
Date of Preconditioning:	9/08/2022	16/08/2022
Date in Freezer (-15°C):	16/08/2022	23/08/2022
Date of Test:	25/08/2022	-

TABLE 10 DURABILITY TEST RESULTS - TEMPERATURE RESISTANCE**Temperature Resistance Specimens**

	Average Break Force (N)	Average Thickness (mm)	Average Tensile strength (F/A) (MPa)	Average Elongation at break		PASS/FAIL
				(mm)	(%)	
7 day period @ 85°C	36.52	1.35	2.70	557.17	1114	PASS
7 day period @ -15°C	37.75	1.35	2.80	502.05	1004	PASS

Observations: No defect

Table A4: Pass / Fail and Criteria compared with control samples

PASS – Elongation at break shall not be less than 50% retention of elongation at break of the controls

Enviro 700x - 8454




FIGURE 3 IMAGES OF TEST SAMPLE PERFORMING DURABILITY LOAD / ELONGATION TEST

5.4 ASTM C794:2018 Standard test method for adhesion-in-peel of elastomeric joint sealants

The measured dimensions of the test samples placed in the test rig stand are shown in Table 11, below.

	In	Out
Date of Preconditioning:	5/09/2022	27/09/2022
Date of test:	27/09/2022	27/09/2022

TABLE 11 ADHESION-IN-PEEL STRENGTH TEST RESULTS

Concrete Substrate				
Specimen No.	Length and width of Test Specimen (mm)	Peel Adhesion Strength in Dry Conditions (N)	Adhesive Loss (%)	Failure Type
8454/52	100x25	168.58	30 & 70	Adhesive Failure & Mesh Failure Cohesive Failure Adhesive Failure Adhesive Failure
8454/53	100x25	128.27	100	
8454/54	100x25	220.60	100	
8454/55	100x25	173.38	100	
	Mean	172.71		




FIGURE 4 IMAGES OF TEST SAMPLE PERFORMING ADHESION-IN-PEEL

Enviro 700x - 8454

5.5 AS/NZS 4347.9:1995 (Reconfirmed) 2014 Damp-proof courses and flashings— Methods of test, Method 9: Determining thickness

The sheet thickness measured at three points, equally spaced across the strip. The specimens tested in a conditioning room maintained at a temperature of $23 \pm 2^\circ\text{C}$ and $60 \pm 5\%$ relative humidity are shown in Table 12, below.

	In	Out
Date of Preconditioning:	27/07/2022	29/07/2022
Date of test:	29/07/2022	29/07/2022

TABLE 12 DETERMINING THICKNESS TEST RESULTS

Specimen No.	Length and Width of Test Specimen (mm)	Thickness (mm)
8454/49	290 x 50	1.37
8454/49	290 x 50	1.34
8454/49	290 x 50	1.31
8454/50	290 x 50	1.39
8454/50	290 x 50	1.34
8454/50	290 x 50	1.30
8454/51	290 x 50	1.41
8454/51	290 x 50	1.39
8454/51	290 x 50	1.33
	Mean	1.35

Enviro 700x - 8454

6. Comments

The Test Sample, as described, when subjected to the test methods of:

AS 4654.1:2012 Waterproofing membranes for external above-ground use Part 1: Materials.

Properties:	(a) water vapour transmission	
	(b) cyclic movement	CLASS III
	(c) durability	CLASS III
	(d) bond strength to concrete substrate	
	(e) membrane thickness	

Met the performance criteria

End of report